



LEIGHS C750V2

PRODUCT TECHNICAL DATA

FULL DESCRIPTION	: LEIGHS C750V2 SPECIAL FINISH		
MATERIAL TYPE	: Isocyanate free - Two pack finish based on acrylic epoxy binder system.		
RECOMMENDED USE	: Finish coat for exterior exposed surfaces where retention of gloss is required, and the use of isocyanate products is precluded or undesirable. : Normally used in conjunction with epoxy primers and undercoats.		
ENDORSEMENTS	: Network Rail approved as an Isocyanate free finish. : Highways Agency No: 167		
RECOMMENDED APPLICATION METHODS	Airless Spray : Conventional Spray	Brush	
COLOUR AVAILABILITY	: Full Range.		
FLASH POINT	Base : 34°C	Additive : 33°C	
% SOLIDS BY VOLUME	: 53 ± 3% (ASTM-D2697-91)		
V.O.C.	: 416 gms/litre determined practically in accordance with UK Regulations PG6/23 435 gms/litre calculated from formulation to satisfy EC Solvent Emissions Directive 309 gms/kilo content by weight from formulation, to satisfy EC SED		
TYPICAL THICKNESS	Dry film thickness : 50 microns	Wet film thickness 94 microns	Theoretical coverage 10.6 m ² /ltr*
	* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification.		
PRACTICAL APPLICATION RATES- microns per coat	Airless Spray	Conventional Spray	Brush#
	Dry 50*	50	20 - 40
	Wet 94	94	38 - 75
	* Maximum sag tolerance typically 75µm dry by airless spray. # The actual thickness within the quoted range will depend on many variables including ambient conditions and operator expertise. To ensure full obliteration and maximum opacity, the appropriate undercoat or primer shade should be used.		
AVERAGE DRYING TIMES	At 15°C	At 23°C	At 35°C
To touch	2 hours	1 hour	½ hour
To recoat	6 hours	3 hours	2 hours
To handle	12 hours	6 hours	4 hours
	These figures are given as a guide only. Factors such as air movement and humidity must also be considered.		
RECOMMENDED THINNER	: Cleanser/Thinner No. 5		
RESISTANCE TO	Moisture - Good Acid spillage - Moderate Alkali spillage - Moderate	Aliphatic solvents - Moderate Abrasion - Moderate Weather - Excellent	
RECOMMENDED UNDERCOATS	: C750V2 is compatible with a wide range of epoxy undercoats including: : Epigrip C400V3 Zinc Phosphate Primer/Buildcoat : Epigrip C402V2 Zinc Phosphate Primer/Buildcoat : Epigrip C425V2 Zinc Phosphate Primer/Buildcoat : Epigrip M905 Winterfast Hi-Build Undercoat : C750V2 must be applied over epoxy materials within 4 days at 23°C to ensure satisfactory intercoat adhesion.		
RECOMMENDED TOPCOATS	: Indefinitely self-overcoatable.		
POT LIFE	12 hours at 15°C	8 hours at 23°C	6 hours at 35°C
PACKAGE	: A two component material supplied in separate containers to be mixed prior to use.		
Pack Size	: 20 litre and 5 litre units when mixed.		
Mixing Ratio	: 4 parts base to 1 part additive by volume.		
Weight	: White 1.41 kg/litre (may vary with shade).		
Shelf Life	: 2 years from date of manufacture or 'Use By' date where specified.		

SURFACE PREPARATION:

Ensure surfaces to be coated are clean, dry and free from all surface contamination.

APPLICATION EQUIPMENT:**Airless Spray**

Nozzle Size : 0.33mm (13 thou)
Fan Angle : 65°
Operating Pressure : 176kg/cm² (2500 psi)

The airless spray details given above are intended as a guide only. Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent with satisfactory atomisation. As conditions will vary from job to job, it is the applicators' responsibility to ensure that the equipment in use has been set up to give the best results. If in doubt Sherwin-Williams should be consulted.

Conventional Spray

Nozzle Size : 1.27mm (50 thou)
Atomising Pressure : 3.5kg/cm² (50 psi)
Fluid Pressure : 0.7kg/cm² (10 psi)

The details of atomising pressure, fluid pressure and nozzle size are given as a guide. It may be found that slight variations of pressure will provide optimum atomisation in some circumstances according to the set up in use. Atomising air pressure depends on the air cap in use and the fluid pressure depends on the length of line and direction of feed i.e. horizontal or vertical.

Brush

The material is suitable for brush application. Application of more than one coat may be necessary to give equivalent dry film thickness to a single spray applied coat.

APPLICATION CONDITIONS AND OVERCOATING:

This material should preferably be applied at temperatures in excess of 10°C. In conditions of high relative humidity, ie 80-85% good ventilation conditions are essential. Substrate temperature should be at least 3°C above the dew point and always above 0°C.

At application temperatures below 10°C, drying and curing times will be significantly extended, and spraying characteristics may be impaired.

Application at ambient air temperatures below 5°C is not recommended.

Steelwork coated with Leighs C750V2 Special Finish should be protected from weather for 48-72 hours after application, depending on conditions. Consult Sherwin-Williams if in doubt.

ADDITIONAL NOTES:

Drying times, curing times and pot life should be considered as a guide only.

The curing reaction commences immediately the two components are mixed, and since the reaction is dependent on temperature, the curing time and pot life will be approximately halved by a 10°C increase in temperature and doubled by a 10°C decrease in temperature.

Tropical Use

Leighs C750V2 at the time of mixing should not exceed a temperature of 35°C. Use of this product outside its pot life may result in inferior adhesion properties even if the material appears fit for application. Thinning the mixed product will not alleviate this problem.

It is not advisable to apply this coating when the air and substrate temperatures exceed 45°C. These conditions can introduce paint film formation defects, such as dry spray, bubbling and pinholing etc.

Numerical values quoted for physical data may vary slightly from batch to batch.

HEALTH AND SAFETY:

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this Data Sheet is liable to modification from time to time in the light of experience and of normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.