

Environment (Defined in ISO 12944-2:1998)	Category C2 - Unheated buildings where condensation may occur (inc. most cavities)
Durability (Life to first major maintenance) (See notes below)	Up to 20 years

Surface Preparation	Blast Clean to Sa2½ BS EN ISO 8501-1:2007
Surface Profile	Within the range 50-75 microns typical

Coat	Material	d.f.t. microns
Primer	Epigrip J984 Zinc Rich Primer	50

Notes on this Specification

- 1 ISO12944 states that Durability is not a guarantee time. Durability should be considered as the coating design life, where regular minor maintenance should be scheduled to achieve the required life to first major maintenance
- 2 Dry film thicknesses (d.f.t.) quoted are NOMINAL as defined by BS EN ISO 12944-5.
- 3 The same material is used for site touch up following suitable cleaning and re-preparation of affected areas.
- 4 All materials should be obtained from Sherwin-Williams and must be applied in accordance with our technical data sheets.
- 5 Coated steelwork should be protected to prevent prolonged contact with water, e.g. ponding.
- 6 Limited colour range
- 7 Prolonged exposure to damp conditions may result in zinc salt formation, which is not detrimental to corrosion performance.
- 8 For fire protection systems, please contact your Sherwin-Williams representative.

Prepared By

Date

Email

Phone

Customer

This specification is offered as guidance only. To ensure that the most appropriate materials are used please contact Sherwin-Williams with the project details.